

ASBESTOS

Narrative Clean-up Goal: Remove any loose asbestos and asbestos that may become loose during vessel sinking; remove or seal accessible friable asbestos.

Environmental impacts

Asbestos is a naturally occurring mineral. The environmental impacts caused by asbestos are dependent upon 1) whether asbestos is reduced to fibers or is in a non-friable form; and 2) whether the asbestos is air-borne or water-borne.

Even though adverse impacts from asbestos are largely from inhalation -- which is not expected to be an issue in the marine environment -- vessel preparation should eliminate the possibility of pieces of asbestos breaking free from the vessel during the sinking operation or asbestos materials losing surface integrity after the vessel has been placed as an artificial reef. Loose asbestos pieces can lead to rafting and may be capable of washing ashore. These asbestos pieces could dry up, break apart, and be reintroduced into the atmosphere. Exposure to airborne asbestos can negatively impact human health via inhalation.

Once a vessel has settled on the ocean floor, asbestos remaining on the vessel (e.g., intact and undisturbed asbestos insulation) will be covered with bacteria over time. This in turn will cause the asbestos fibers to sink and remain contained within the reef matrix, minimizing any potential direct impacts to the marine environment. (see Appendix C)

What is asbestos?

Asbestos refers to a group of minerals that occur naturally as masses of long silky fibers. There are three main types of asbestos fibers:

- Chrysotile fibers (white asbestos) are fine, silky flexible white fibers. They are pliable and cylindrical, and arranged in bundles. This was the most commonly used asbestos in the United States.
- Amosite fibers (brown asbestos) are straight, brittle fibers that are light grey to pale brown. This was the most commonly used asbestos in thermal system insulation.
- Crocidolite fibers (blue asbestos) are straight blue fibers that are like tiny needles.

There are three other types of asbestos fibers: anthophyllite, tremolite, and actinolite. Unlike most minerals, which turn into dust particles when crushed, asbestos breaks up into fine fibers that may be too small to be seen by the human eye.

Individual asbestos fibers are often mixed with a material that binds them together, forming what is commonly called asbestos-containing material (ACM). There are two kinds of ACM: Friable

DRAFT DRAFT DRAFT DRAFT DRAFT DRAFT
and non-friable.

- **Friable ACM** is any material containing more than 1% asbestos that, when dry, may be crumbled, pulverized, or reduced to powder by hand pressure.
- **Non-friable ACM** is any material containing more than 1% asbestos that, when dry, cannot be crumbled, pulverized, or reduced to powder by hand pressure. Non-friable ACM is divided into two categories.
 1. **Category I** non-friable ACM includes asbestos-containing resilient floor coverings, packings, and gaskets.
 2. **Category II** non-friable ACM includes all other non-friable ACM that is not included in Category I.

Asbestos is resistant to abrasion and corrosion, inert to acid and alkaline solutions, and stable at high temperatures. It is strong yet flexible, non-combustible, conducts electricity poorly, and is an effective thermal insulator.

Where is asbestos found on a ship?

Asbestos on ships may be found in many materials, including, but not limited to:

- Bulkhead and pipe thermal insulation
- Bulkhead fire shields/fireproofing
- Uptake space insulation
- Exhaust duct insulation
- Electrical cable materials
- Brake linings
- Floor tiles and deck underlay
- Overhead and panel sheeting (cement and cellulose based)
- Steam, water, and vent flange gaskets
- Adhesives and adhesive-like glues (e.g., mastics) and fillers
- Sound damping
- Molded plastic products (e.g., switch handles, clutch facings)
- Sealing Putty
- Packing in shafts and valves
- Packing in electrical bulkhead penetrations
- Asbestos arc chutes in circuit breakers
- Pipe hanger inserts
- Weld shop protectors and burn covers, blankets, and any fire-fighting clothing or equipment
- Any other type of thermal insulating material

NOTE: Asbestos-containing material may be found underneath materials that do not contain

DRAFT DRAFT DRAFT DRAFT DRAFT DRAFT
asbestos. Thermal system insulation and surfacing material found in vessels and vessel sections constructed after 1980 may be presumed to be free of asbestos containing material.

Vessel Preparation

Asbestos can be found throughout ships, from the bridge to the bottom of the bilge. Identifying the locations and types of asbestos onboard are essential for vessel preparation and should be considered early in the clean-up process. Once the type and location of asbestos and asbestos containing materials are identified, a determination should be made whether to remove, encapsulate, or leave the asbestos undisturbed.

The method of demolition is particularly important to the effective management of asbestos on board ships. If the sinking method for the vessel includes the use of explosives, asbestos-containing material that may become disturbed during detonation should be removed from the vessel.

In addition, any asbestos that is moved or disturbed (including during clean-up operations) or can potentially get dislodged as the vessel sinks should be removed from the vessel. Friable asbestos should be sealed as a precautionary measure to prevent releases of asbestos in high concentrations during the sinking event. Intact and undisturbed asbestos insulation need not be removed.

Engine Room and Engine Compartments

Removal or encapsulation of exposed, disturbed and deteriorated asbestos should be considered since it is likely that the asbestos will break free and create debris during sinking. If the asbestos is to be encapsulated, its integrity should not be impacted by the preparation for sinking as well as the sinking itself.

The primary source of friable asbestos is found on pipe wrappings around the main boilers and steam fittings. On most vessels the asbestos coating, which is 1 to 3 inches thick, is covered with canvas and is usually painted. If work needs to be done around the piping and the covering, causing the asbestos to be disturbed, the disturbed material should be removed. If the covering is deteriorated and it is likely that the asbestos will break free during sinking, then removal or encapsulation with an epoxy or other non-water soluble and non-toxic sealer should be considered.

Certain boilers and piping are covered with a very friable asbestos paste. Throughout the engine room there are numerous asbestos gaskets connecting piping and ductwork. If left intact, these gaskets usually will not release asbestos fibers. However, if the ductwork or piping needs to be cut or removed and vessel debris is created as a result, gaskets should be removed or encapsulated if possible.

In some engine rooms asbestos/cellulose sheets are found behind power and electrical panels or in the overhead where electrical service passes. Undisturbed, this material is not friable. However, once the sheets are exposed to the marine environment, the sheets lose their integrity and can break up and raft. Where possible, these sheets should be removed. Note that asbestos

cement sheets may also be used as panels on the vessel. However, these sheets are not water-soluble and therefore should not break apart when exposed to the marine environment. These sheets can stay in place unless cut, drilled or disturbed. Friable asbestos may also be found between bulkheads; this asbestos may remain in place because the asbestos is contained within the bulkheads. If, however, the bulkheads are drilled, cut, or disturbed, the friable asbestos that is now exposed should be encapsulated or removed.

Ship Interior and Living Spaces

Asbestos was also used in some hatch gaskets mixed with rubber throughout ships, especially in watertight spaces. Under normal circumstances this will only present a problem if grinders or torches are used. In such cases, the gaskets should be removed prior to disturbance.

Asbestos/asphalt floor tile was common from the 1940's to the mid 1970's. This form of asbestos is manufactured with the asbestos encapsulated. If preparation of the vessel requires the tile to be disturbed via grinding, cutting, or burning, those pieces of tile should be removed. Asbestos sheets both with cement and cellulose may be found especially in the combat information center, the radio room and other spaces where electrical equipment may be found. Cellulose/asbestos panels should be removed but cement panels are safe. As an example, while inspecting an old Navy tug planned for reefing off the coast of Virginia, it was determined that the entire interior of the wheel house was paneled with cellulose/asbestos panels and had to be removed.

Exterior Spaces

There are a few areas on the exterior of ships where asbestos was used. Asbestos may have been mixed with paint and applied as a coating near some vents and hatches. Also, some hatches may have gaskets that contain asbestos. In either case, the material does not need to be removed unless these exterior areas require grinding or cutting.