



United States  
Department of  
Agriculture

Forest Service

Forest  
Products  
Laboratory

Research  
Paper  
FPL-RP-673



# Performance Characteristics of Borate Fatty Acid Formulations as Mold Inhibitors

Robert D. Coleman

Vina W. Yang

Carol A. Clausen



## Abstract

The combination of boric acid (BA) or disodium octaborate tetrahydrate (DOT) and a fatty acid (FA) such as heptanoic, octanoic, and nonanoic acids (C7–C9) is an effective treatment solution for protecting wood structures against mold. BA or DOT alone have substantial potency against insects and decay fungi, but have negligible or no mold inhibitor activity. However, boric acid or DOT combined with a fatty acid either as a dip or vacuum treatment appears to act synergistically to inhibit mold growth. Southern Pine vacuum-treated with BA (or DOT)/FA appears to retain much or all of its inhibitor properties after extensive leaching with water. Boric acid/FA and DOT/FA formulations applied as dip solutions had similar efficacy against the test fungi, but greater efficacy as a mold inhibitor was achieved when DOT was formulated with C7, C8, or C9 FA and used as a vacuum treatment.

Keywords: fatty acid, boric acid, disodium octaborate tetrahydrate, mold fungi, fungicide

## Acknowledgment

The information contained in this paper is based upon a USDA SBIR Phase II award to Summerdale, Inc., supported by the National Institute of Food and Agriculture, U.S. Department of Agriculture, “Organic Acid Formulations for Wood Protection: Inhibition of Mold and Decay Fungi.”

March 2013

---

Coleman, Robert D.; Yang, Vina W.; Clausen, Carol A. 2013. Performance characteristics of borate fatty acid formulations as mold inhibitors. Research Paper FPL-RP-673. Madison, WI: U.S. Department of Agriculture, Forest Service, Forest Products Laboratory. 6 p.

A limited number of free copies of this publication are available to the public from the Forest Products Laboratory, One Gifford Pinchot Drive, Madison, WI 53726–2398. This publication is also available online at [www.fpl.fs.fed.us](http://www.fpl.fs.fed.us). Laboratory publications are sent to hundreds of libraries in the United States and elsewhere.

The Forest Products Laboratory is maintained in cooperation with the University of Wisconsin.

The use of trade or firm names in this publication is for reader information and does not imply endorsement by the United States Department of Agriculture (USDA) of any product or service.

The USDA prohibits discrimination in all its programs and activities on the basis of race, color, national origin, age, disability, and where applicable, sex, marital status, familial status, parental status, religion, sexual orientation, genetic information, political beliefs, reprisal, or because all or a part of an individual’s income is derived from any public assistance program. (Not all prohibited bases apply to all programs.) Persons with disabilities who require alternative means for communication of program information (Braille, large print, audiotape, etc.) should contact USDA’s TARGET Center at (202) 720–2600 (voice and TDD). To file a complaint of discrimination, write to USDA, Director, Office of Civil Rights, 1400 Independence Avenue, S.W., Washington, D.C. 20250–9410, or call (800) 795–3272 (voice) or (202) 720–6382 (TDD). USDA is an equal opportunity provider and employer.

## Contents

|   |   |
|---|---|
| Introduction.....                                     | 1 |
| Materials and Methods.....                            | 1 |
| Chemicals.....  | 1 |
| Treatment .....                                       | 1 |
| Mold and Sapstain Fungi and Inoculum Preparation..... | 1 |
| Chemical Leaching .....                               | 2 |
| Mold and Sapstain Test.....                           | 2 |
| Results.....  | 2 |
| Discussion and Conclusions .....                      | 2 |
| References.....                                       | 3 |
| Tables .....  | 4 |

# Performance Characteristics of Borate Fatty Acid Formulations as Mold Inhibitors

**Robert D. Coleman**, President  
Summerdale, Inc., Verona, Wisconsin

**Vina W. Yang**, Microbiologist  
**Carol A. Clausen**, Supervisory Research Microbiologist  
Forest Products Laboratory, Madison, Wisconsin

## Introduction

Current insecticides and fungicides used to protect wood from biodeterioration are effective but may be toxic and unsuitable for use in modern homes, especially those sealed and insulated to reduce the exchange of hot or cold air from the outside. Another concern to human health in modern homes is exposure to mold (Quarles 2008). Spores from mold fungi can be particularly problematic, not only as human and animal allergens, but also because of their recalcitrance to chemical remediation. Among the three primary wood infestations (termite attack, mold, and decay fungi), spores from mold fungi appear to be the most resistant to chemical treatments; hence, mold spores are more difficult to suppress and control (Clausen and Yang 2004).

Earlier work revealed that aliphatic mono-carboxyl compounds such as fatty acids are active against a broad spectrum of fungal pathogens (Kabara and others 1972; Walters and others 2004). Lauric acid, a saturated C12 fatty acid (Kabara and others 1972), and linoleic and linolenic acids, unsaturated C18 fatty acids (Walters and others 2004), had antifungal properties.

Lower molecular weight aliphatic, saturated fatty acids, such as pentanoic, hexanoic, heptanoic, octanoic, nonanoic, and decanoic acids (C5–C10, respectively) have also been studied for control of numerous fungi (Coleman 2010a,b; 2011) including mold and decay fungi (Schmidt 1982; Coleman and Clausen 2009; Clausen and others 2010; Coleman and others 2010a,b). Formulations, at various application rates, have been tested with and without selected adjuvants such as organic acids (L-lactic and glycolic acid). Although exclusive use of organic acids as broad-spectrum biocides has not been effective for long-term control of mold and other fungi, their potential as synergists with certain fatty acids may result in the development of broad-spectrum, environmentally compatible fungicides.

This study evaluated the efficacy of multifunctional fatty acid/boric acid (or disodium octaborate tetrahydrate (DOT)) combinations against common mold species on wood. Antimicrobial formulations having multiple mechanisms of action with greater formulation potency and improved retention characteristics would be considerably more efficacious. The fatty acid/boric acid (or DOT) combination

may provide cost effective and safe performance required by the construction industry and the public's environmental and health concerns. The research was conducted under a joint venture agreement between Summerdale, Inc., and Forest Products Laboratory (FPL).

## Materials and Methods

### Chemicals

Various combinations of the following chemicals were evaluated: Boric acid and DOT (U.S. Borax, Inc., RioTinto Minerals, Greenwood Village, CO, USA), octanoic acid, nonanoic acid and capric acid (Emery Oleochemicals, Cincinnati, OH, USA), hexanoic acid (Acros Organics, Geel, Belgium), heptanoic acid (Sigma-Aldrich, St. Louis, MO, USA), glycerol (U.S. Glycerin, Kalamazoo, MI, USA), L (+) lactic acid (Purac FCC, Lincolnshire, IL, USA), mineral oil (Fisher Scientific, Pittsburgh, PA, USA), and PE 1198LA, a phosphate ester emulsifier (Huntsman Chemical, The Woodlands, TX, USA).

### Treatment

Kiln-dried Southern Pine (SP) specimens (7 by 20 mm cross section by 7 cm long) were soaked overnight in deionized (DI) water to elevate moisture content prior to dip or vacuum treatment. Groups of specimens were dip-treated for ~30 s in each chemical formulation and held overnight in a closed container according to the ASTM standard test method D4445-10 (ASTM 2010) or ASTM D3273-12 (ASTM 2012) prior to exposure to test fungi. Vacuum treatments were conducted according to a modification of AWPA T1-07 (2007). Briefly, specimens were submerged in treatment solution and held under vacuum (-172 kPa) for 70 min. Vacuum-treated specimens were air-dried and conditioned at 27° C and 70% RH to a constant weight before exposing them to test fungi.

### Mold and Sapstain Fungi and Inoculum Preparation

Mold fungi, *Aspergillus niger* 2.242, *Penicillium chrysogenum* PH02, *Alternaria alternata*, and *Trichoderma atroviride* ATCC 20476, were grown on 2% malt agar and individual spore suspensions prepared by washing the surface of a 2-wk-old culture of each fungus with 10 mL

of sterile DI water according to ASTM standard D4445-10 (ASTM 2010). Spore suspensions were transferred to a spray bottle and diluted to 100 mL with DI water to yield approximately  $10^7$  spores mL<sup>-1</sup>. The spray bottle was adjusted to deliver 1 mL inoculum/spray. The sapstain fungus, *Aureobasidium pullulans*, was grown on 2% potato dextrose agar and an individual spore suspension was prepared from a 2-wk-old culture according to ASTM D4445-10.

### Chemical Leaching

Leaching procedures were similar to AWPA E11-06 standard method (AWPA 2009). After conditioning, treated specimens were placed into a 500-mL glass container, submerged in 100 mL of DI water, and subjected to mild agitation for a total of 14 days, and with a complete water change after 6 h, and at 1, 2, 4, 6, 8, 10, 12, and 14 days. Leached and unleached specimens were exposed to mold and sapstain testing.

### Mold and Sapstain Test

Twelve random replicate treated specimens were arranged over four layers of blotting paper saturated with 30-mL DI water and a polyethylene mesh spacer in sterile disposable Petri dishes (150 by 25 mm) (B-D Falcon, Los Angeles, CA, USA). Untreated specimens dipped in DI water served as controls. Specimens were sprayed with 1 mL of individual mold or sapstain spore inoculum, sealed in polyethylene bags to prevent drying, and incubated at 27 °C and 70% RH for 8 to 12 wk.

## Results

Certain fatty acids and boric acid (or DOT), in selected combinations, appear to be more effective as mold inhibitors than the fatty acid alone. Since mold inhibition of leached SP matched that of unleached SP, sufficient boric acid (DOT)/FA appeared to be retained in vacuum-treated, leached SP. The efficacy of DOT as a means to improve mold-inhibiting activity of an octanoic acid (C8) formulation is shown in Table 1. Specifically, DOT at two rates (0.25%, 2.00%, g/v) in aqueous solutions were compared to water alone as the carrier solution for the C8 formulation. Although both DOT carrier solutions alone (treatments 4, 5) had an absence of mold protection, DOT combined with the C8 formulation (treatments 2, 3) improved mold-inhibiting activity slightly over using water as the carrier.

Boric acid (0.25%, g/v) also appeared to be synergistic with fatty acids in dip treatments (Table 2). Boric acid alone (treatment 5) was ineffective as a mold inhibitor when compared to water control (treatment 6). However, when the boric acid solution was compared to water as the carrier solution and amended with either a C8 or C9 formulation, boric acid had increased efficacy against test fungi. This finding suggested that the increase in efficacy was synergistic rather than additive. Protection from mold growth after exposure

to a C8- or C9-based treatment without boric acid was essentially equivalent. Fatty acid (C8/C10) mold-inhibiting formulations with and without DOT were compared at two application rates (3%, 12%, v/v). Dip treatments inclusive of DOT (treatments 3, 4) were more effective than treatments without DOT at both rates (Table 3).

Vacuum treatments of SP using fatty-acid-based boric acid formulations were effective at all three application rates (6%, 12%, and 18%, v/v). This was true for both C9 and C8/C10 where nearly complete control of mold growth was observed at 4, 8, and 12 wk (Table 4).

Mold test results for specimens that were vacuum-treated with fatty acids and boric acid (or DOT), followed by water leaching, suggested that certain fatty acid species were retained in SP and performed better as mold inhibitors than other species (Table 5). In particular, C8 (treatments 3, 8) and C9 (treatments 4, 9) were more effective. Overall, DOT-fatty acids were more efficacious than formulations containing boric acid. An absence of mold growth was evident at 4–12 wk for DOT/C7 – C9 (treatments 7–9).

Table 6 revealed inhibition of mold growth after dip applications with the same formulations and rate tested in vacuum treatments (Table 5). Overall dip treatments, including boric acid and DOT, had similar levels of mold inhibition. However, C7 formulations (treatments 2, 7) were more effective and resulted in control of mold growth through 12 wk. The other fatty acid species (C6, C8, C9, C8/C10) reduced mold by more than 90% at 4 and 8 wk; quite possibly, these fatty acid formulations could be reformulated to match the fungicide activity of C7.

To investigate fatty acid/borate inhibition of sapstain (Table 7), a C8/C10-based preparation was supplemented with DOT at various concentrations (2%, 4% and 6%, g/v). At 12%, v/v, all formulations (treatments 1–4) decreased growth of the sapstain fungus compared to the control (treatment 5). Formulations containing 4% and 6% DOT (treatments 3–4) completely inhibited sapstain at 12 wk.

## Discussion and Conclusions

DOT is used worldwide for treating wood (Lloyd and Manning 1995). In the United States, Australia, and South Africa, borates such as DOT are commonly used for treating timber-framed constructions. This natural mineral has a record of human and aquatic safety, is very inexpensive, and does not corrode metal (Schultz and Nicholas 2003). DOT is relatively soluble in water and thus has good penetration of all major structural lumber species in the United States. Moreover, DOT treatments are compliant with major building codes and in general are noncorrosive to most metal nails, screws and fasteners.

Boric acid and DOT leaching can occur with exposure to water, thus restricting the bulk of current treatments of

boron compounds to indoor construction. As a result, treated lumber exposed to rainfall (leaching conditions) over time loses substantial amounts of boric acid or DOT, reducing its effectiveness as a preservative. Although DOT has demonstrated capability in combating insects and decay fungi (Drysdale 1994), it has very limited ability to inhibit mold (Barnes and others 1989). Five percent DOT was unable to substantially inhibit mold fungi (Clausen and Yang 2003). Current and past efforts to fix boric acid and DOT within the wood structure often result in a loss of activity.

The fatty acid/boric acid (DOT) combination, upon extensive leaching, was substantially retained in treated wood. Sufficient amounts of fatty acid/ boric acid (DOT), as active ingredients for control of wood mold, remain in treated wood after repeated and prolonged exposure to water. Leached wood containing the fatty acid/boric acid (or DOT) combination had substantially the same fungicidal activity as an unleached wood sample suggesting that the formulation is suitable for limited UC2 and UC3A exposure. Finally, the fatty acid/boric acid (DOT) combinations exhibited synergistic efficacy against test fungi.

## References

- ASTM. 2012. Standard test method for resistance to growth of mold on the surface of interior coatings in an environmental chamber. ASTM D3273-12. West Conshohocken, PA: American Society for Testing Materials. Vol. 06.01. pp. 411–413.
- ASTM. 2010. Standard test method for fungicides for controlling sapstain and mold on unseasoned lumber (Laboratory Method). D4445–10. In: Annual Book of Standards, Vol. 4.10., West Conshohocken, PA: American Society for Testing Materials. pp. 496–500.
- AWPA. 2007. Standard AWPA T1-07. Processing and treatment standard (pressure treatment methodology). Birmingham, AL: American Wood Protection Association.
- AWPA. 2009. Standard method of determining the leachability of wood preservatives. E11-06. In: AWPA Book of Standards, Birmingham, AL: American Wood Protection Association. pp. 389–391.
- Barnes H.M., Amburgey, T.L., Williams, L.H., Morrell, J.J. 1989. Borates as wood preserving compounds: The status of research in the United States. IRG/WP/3542. International Research Group on Wood Preservation, Stockholm, Sweden.
- Clausen, C.A., Yang, V.W. 2003. Mold inhibition on unseasoned southern pine. IRG/WP 03–10465. Stockholm, Sweden: International Research Group on Wood Preservation.
- Clausen, C.A., Yang, V.W. 2004. Multicomponent biocide systems protect wood from decay fungi, mold fungi, and termites for interior applications. IRG/WP 04-30333. Stockholm, Sweden: International Research group on Wood Protection.
- Clausen, C.A., Coleman, R.D. Yang, V.W. 2010. Fatty acid formulations for wood protection. *Forest Products Journal*. 60: 301–304.
- Coleman, R.D. 2010a. Coleman Fungicide Compositions. U.S. Patent 7,741,244.
- Coleman, R.D. 2010b. Pesticide Compositions and Methods for Their Use. U.S. Patent 7,820,594.
- Coleman, R.D. Clausen, C.A. 2009. Multi-factorial antimicrobial wood protectants. IRG/WP 08-30484. Stockholm, Sweden: International Research Group on Wood Protection.
- Coleman, R.D., Yang, V.W., Woodward, B., Lebow, P., Clausen, C.A. 2011. Efficacy of fatty acid chemistry: Candidate mold and decay fungicides. *Proceedings of American Wood Protection Association*, Birmingham, AL. 106: 287–297.
- Drysdale, J.A. 1994. Boron treatments for the preservation of wood—A review of efficacy data for fungi and termites. IRG/WP 94-30037. Stockholm, Sweden: International Research Group on Wood Preservation.
- Kabara, J.J., Swieczkowski, D.M., Conly, A.J., Truant, J.P. 1972. Fatty acids and derivatives as antimicrobial agents. *Antimicrobial Agents and Chemotherapy*. 2(1): 23–28.
- Lloyd, J.D., Manning, M.J. 1995. Leaching of boron wood preservatives—a reappraisal. *Proceedings of the British Wood Preserving and Damp Proofing Association*. 7p.
- Quarles, S.L. 2008. Mold growth in structures: an overview. In: *Development of commercial wood preservatives*. Schultz, T.P., Militz, H., Freeman, M., Goodell, B. and D.D. Nicholas (Eds.) American Chemical Society, Washington, D.C. pp. 170–181.
- Schmidt, E.L. 1982. Influence of aliphatic fatty acids on spore germination of wood decay fungi. IRG/WP/2224. International Research Group on Wood Preservation, Stockholm, Sweden.
- Schultz, T.P., Nicholas, D.D. 2003. A brief overview of non-arsenical wood preservative systems. Chapter 26. In: *Wood deterioration and preservation; Advances in our changing world*. Goodell, B., Nicholas, D.D. and T.P Schultz (Eds.), American Chemical Society, Washington, D.C. pp. 420–432.
- Walters, D., Raynor, L., Mitchell, A., Walker, R., Walker, K. 2004. Antifungal activities of four fatty acids against plant pathogenic fungi. *Mycopathologia* 157: 87–90.

**Table 1. Mold inhibition in SP dip-treated with disodium octaborate tetrahydrate and C8 fatty acid**

| Treatment group | Formulation     | Concentration (%) | Carrier     | Rating <sup>a</sup> (12 wk) | FPLSD <sup>b</sup> <i>P</i> @0.05 |
|-----------------|-----------------|-------------------|-------------|-----------------------------|-----------------------------------|
| 1               | C8 <sup>c</sup> | 6.00              | Water       | 0.83                        | a                                 |
| 2               | C8              | 6.00              | DOT (0.25%) | 0.58                        | a                                 |
| 3               | C8              | 6.00              | DOT (0.25%) | 0                           | a                                 |
| 4               | DOT             | 0.25              | Water       | 3.40                        | b                                 |
| 5               | DOT             | 2.00              | Water       | 3.33                        | b                                 |
| 6               | Control         | —                 | Water       | 3.00                        | b                                 |

<sup>a</sup>Average mold growth based on a rating system where 0 is no growth and 1, 2, 3, 4, and 5 represent 20%, 40%, 60%, 80%, and 100% growth, respectively.

<sup>b</sup>FPLSD: Fisher's protected least significant difference; same letters are not significant at *P* < 0.05.

<sup>c</sup>50% C8, 20% phosphate ester (PE) 1198, 10% L-lactic acid, 20% mineral oil.

**Table 2. Mold inhibition on SP dip-treated with boric acid and C8 or C9 fatty acids**

| Treatment group | Formulation     | Concentration (%) | Carrier            | Rating <sup>a</sup> (12 wk) | FPLSD <sup>b</sup> <i>P</i> @0.05 |
|-----------------|-----------------|-------------------|--------------------|-----------------------------|-----------------------------------|
| 1               | C8 <sup>c</sup> | 6.00              | Water              | 0.90                        | b                                 |
| 2               | C8              | 6.00              | Boric acid (0.25%) | 0.33                        | b                                 |
| 3               | C9 <sup>d</sup> | 6.00              | Water              | 0.80                        | b                                 |
| 4               | C9              | 6.00              | Boric acid (0.25%) | 0.33                        | b                                 |
| 5               | Boric acid      | 0.25              | Water              | 3.91                        | a                                 |
| 6               | Control         | —                 | Water              | 3.50                        | a                                 |

<sup>a</sup>Average mold growth based on a rating system where 0 is no growth and 1, 2, 3, 4, and 5 represent 20%, 40%, 60%, 80%, and 100% growth, respectively.

<sup>b</sup>FPLSD: Fisher's protected least significant difference; same letters are not significant at *P* < 0.05.

<sup>c</sup>50% C8, 20% phosphate ester (PE) 1198, 10% L-lactic acid, 20% mineral oil.

<sup>d</sup>50% C8, 20% PE 1198, 10% L-lactic acid, 20% mineral oil.

**Table 3. Mold inhibition of SP dip-treated with C8/C10-based formulations with and without DOT**

| Treatment group | Aqueous formulation          | Concentration (% v/v) | Rating <sup>a</sup> (12 wk) |
|-----------------|------------------------------|-----------------------|-----------------------------|
| 1               | C8/C10 <sup>b</sup>          | 3.0                   | 1.33                        |
| 2               | C8/C10                       | 12.0                  | 0.33                        |
| 3               | C8/C10 plus DOT <sup>c</sup> | 3.0                   | 0.58                        |
| 4               | C8/C10 plus DOT              | 12.0                  | 0.25                        |
| 5               | Control, water               | —                     | 2.00                        |

<sup>a</sup>Average mold growth based on a rating system where 0 is no growth and 1, 2, 3, 4, and 5 represent 20%, 40%, 60%, 80%, and 100% growth, respectively.

<sup>b</sup>50% C8/C10, 20% phosphate ester (PE) 1198LA, 30% mineral oil.

<sup>c</sup>50% C8/C10, 20% PE 1198LA, 10% mineral oil, 4% DOT, 16% glycerol.

**Table 4. Mold inhibition of SP vacuum-treated with varying concentrations of C9 or C8/C10-boric acid formulations**

| Treatment group | Formulation         | Concentration (% v/v) | Mold rating <sup>b</sup> |      |       |
|-----------------|---------------------|-----------------------|--------------------------|------|-------|
|                 |                     |                       | 4 wk                     | 8 wk | 12 wk |
| 1               | C9 <sup>c</sup>     | 6.0                   | 0                        | 0    | 0     |
| 2               | C9                  | 12.0                  | 0                        | 0    | 0     |
| 3               | C9                  | 18.0                  | 0                        | 0    | 0     |
| 4               | C8/C10 <sup>d</sup> | 6.0                   | 0                        | 0    | 0     |
| 5               | C8/C10              | 12.0                  | 0                        | 0    | 0.08  |
| 6               | C8/C10              | 18.0                  | 0                        | 0    | 0     |
| 7               | Control, water      | —                     | 3.00                     | 3.75 | 3.92  |

<sup>a</sup>Vacuum treatment at -172 kPa for 70 min.

<sup>b</sup>Average mold growth based on a rating system where 0 is no growth and 1, 2, 3, 4, and 5 represent 20%, 40%, 60%, 80%, and 100% growth, respectively.

<sup>c</sup>50% C9, 20% phosphate ester (PE) 1198LA, 6% boric acid, 24% glycerol.

<sup>d</sup>50% C8/C10, 20% PE 1198LA, 6% boric acid, 24% glycerol.

**Table 5. Fatty acids + boric acid (or DOT) as mold inhibitors on SP vacuum-treated<sup>a</sup> and then leached in water, replicate trials A and B**

| Treatment group | Aqueous formulation (18% v/v) | Mold rating <sup>b</sup> |                      |      |         |         |      |         |         |      |
|-----------------|-------------------------------|--------------------------|----------------------|------|---------|---------|------|---------|---------|------|
|                 |                               | 4 wk                     |                      |      | 8 wk    |         |      | 12 wk   |         |      |
|                 |                               | Trial A <sup>c</sup>     | Trial B <sup>c</sup> | Avg  | Trial A | Trial B | Avg  | Trial A | Trial B | Avg  |
| 1               | 50% C6 <sup>d</sup>           | 0.83                     | 0.16                 | 0.48 | 3.00    | 0.66    | 1.83 | 3.66    | 2.60    | 3.13 |
| 2               | 50% C7 <sup>d</sup>           | 0.16                     | 0                    | 0.08 | 0.50    | 0       | 0.25 | 2.33    | 0.16    | 1.25 |
| 3               | 50% C8 <sup>d</sup>           | 0                        | 0.16                 | 0.08 | 0       | 0.16    | 0.08 | 1.00    | 1.00    | 1.00 |
| 4               | 50% C9 <sup>d</sup>           | 0                        | 0                    | 0    | 0       | 0       | 0    | 0.16    | 0.50    | 0.33 |
| 5               | 50% C8/C10 <sup>d</sup>       | 0.16                     | 0                    | 0.08 | 0.66    | 0.16    | 0.41 | 1.33    | 1.66    | 1.49 |
| 6               | 50% C6 <sup>e</sup>           | 0.16                     | 0                    | 0.08 | 0.16    | 0       | 0.08 | 1.33    | 1.33    | 1.33 |
| 7               | 50% C7 <sup>e</sup>           | 0                        | 0                    | 0    | 0       | 0       | 0    | 0       | 0       | 0    |
| 8               | 50% C8 <sup>e</sup>           | 0                        | 0                    | 0    | 0       | 0       | 0    | 0       | 0       | 0    |
| 9               | 50% C9 <sup>e</sup>           | 0                        | 0                    | 0    | 0       | 0       | 0    | 0       | 0       | 0    |
| 10              | 50% C8/C10 <sup>e</sup>       | 0                        | 0                    | 0    | 0       | 0       | 0    | 0.32    | 0       | 0.16 |
| 11              | Control, water                | 1.00                     | 1.16                 | 1.08 | 2.50    | 2.00    | 2.25 | 2.66    | 2.50    | 2.61 |

<sup>a</sup>Vacuum treatments at -172 kPa for 70 min.

<sup>b</sup>Average mold growth based on a rating system where 0 is no growth and 1, 2, 3, 4, and 5 represent 20%, 40%, 60%, 80%, and 100% growth, respectively.

<sup>c</sup>*n* = 12.

<sup>d</sup>Additional formulation components 20% phosphate ester (PE) 1198LA, 6% boric acid, 24% glycerol.

<sup>e</sup>Additional formulation components 20% phosphate ester (PE) 1198LA, 30% boric acid, 24% glycerol.

**Table 6. Comparison of fatty acids combined with boric acid (or DOT) as mold inhibitor on dip-treated Southern Pine, replicate trials A and B**

| Treatment group | Aqueous formulation (18% v/v) | Mold rating <sup>a</sup> |                      |      |         |         |      |         |         |      |
|-----------------|-------------------------------|--------------------------|----------------------|------|---------|---------|------|---------|---------|------|
|                 |                               | 4 wk                     |                      |      | 8 wk    |         |      | 12 wk   |         |      |
|                 |                               | Trial A <sup>b</sup>     | Trial B <sup>b</sup> | Avg  | Trial A | Trial B | Avg  | Trial A | Trial B | Avg  |
| 1               | 50% C6 <sup>c</sup>           | 0.33                     | 0                    | 0.16 | 0.50    | 0       | 0.25 | 0.32    | 0       | 0.16 |
| 2               | 50% C7 <sup>c</sup>           | 0                        | 0                    | 0    | 0       | 0       | 0    | 0       | 0       | 0    |
| 3               | 50% C8 <sup>c</sup>           | 0.16                     | 0                    | 0.08 | 0.16    | 0       | 0.08 | 0.16    | 0       | 0.08 |
| 4               | 50% C9 <sup>c</sup>           | 0.16                     | 0                    | 0.08 | 0.32    | 0       | 0.16 | 0.32    | 0.16    | 0.24 |
| 5               | 50% C8/C10 <sup>c</sup>       | 0.66                     | 0                    | 0.33 | 0.66    | 0       | 0.33 | 1.00    | 0       | 0.50 |
| 6               | 50% C6 <sup>d</sup>           | 0                        | 0.16                 | 0.08 | 0       | 0.32    | 0.16 | 0       | 0.32    | 0.16 |
| 7               | 50% C7 <sup>d</sup>           | 0                        | 0                    | 0    | 0       | 0.16    | 0.08 | 0       | 0       | 0    |
| 8               | 50% C8 <sup>d</sup>           | 0.16                     | 0                    | 0.08 | 0.16    | 0.16    | 0.16 | 1.00    | 0       | 0.50 |
| 9               | 50% C9 <sup>d</sup>           | 0.16                     | 0                    | 0.08 | 0.16    | 0.16    | 0.16 | 0.33    | 0.16    | 0.24 |
| 10              | 50% C68/C10 <sup>d</sup>      | 0.16                     | 0.16                 | 0.16 | 0.32    | 0.32    | 0.32 | 0.66    | 0.83    | 0.75 |
| 11              | Control, water                | 2.50                     | 2.50                 | 2.50 | 3.16    | 2.83    | 3.00 | 3.16    | 3.00    | 3.08 |

<sup>a</sup>Average mold growth based on a rating system where 0 is no growth and 1, 2, 3, 4, and 5 represent 20%, 40%, 60%, 80%, and 100% growth, respectively.

<sup>b</sup>*n* = 12.

<sup>c</sup>Additional formulation components: 20% phosphate ester (PE) 1198LA, 6% boric acid, 24% glycerol.

<sup>d</sup>Additional formulation components: 20% PE 1198LA, 6% DOT, 24% glycerol.

**Table 7. Inhibition of *Aureobasidium pullulans* on SP dip-treated with C8/C10 fatty acid formulations with and without disodium octaborate tetrahydrate**

| Treatment group | Aqueous formulation  | Concentration (% v/v) | Rating <sup>a</sup> (12 wk) |
|-----------------|--|-----------------------|-----------------------------|
| 1               | 50% C8/C10, 20% phosphate ester (PE) 1198LA, 30% mineral oil     | 12                    | 0.25                        |
| 2               | 50% C8/C10, 20% PE 1198LA, 20% mineral oil, 2% DOT, 8% glycerol  | 12                    | 0.16                        |
| 3               | 50% C8/C10, 20% PE 1198LA, 10% mineral oil, 4% DOT, 16% glycerol | 12                    | 0                           |
| 4               | 50% C8/C10, 20% PE 1198LA, 6% DOT, 24% glycerol                  | 12                    | 0                           |
| 5               | Control, water   | —                     | 2.25                        |

<sup>a</sup>Average mold growth based on a rating system where 0 is no growth and 1, 2, 3, 4, and 5 represent 20%, 40%, 60%, 80%, and 100% growth, respectively.

